

CEMENT MORTAR

- Cement mortar 100/300 is designed to be used for building chimney heads, preparing the levelling layers of concrete surfaces.
- The mixture can be used at temperatures +5...+30 C.
- The freshly cast layer must be protected from the rain, freezing and other such damaging impact. AS follow-up maintenance, the surface is covered to prevent it from drying quickly.
- The mixture is best for 12 months after the production date.



STORE IN DRY!



**MAY IRRITATE EYES,
AIRWAYS AND SKIN!**



**AVAILABLE IN BAGS
OF 25 KG AND 1 TON**

Compressive strength	M30
Reaction to fire	A1
Chloride content	≤ 0,02 %
Frost resistance	50 cycles
Yield (25 kg)	12,5 l
Usage period	Up to 4 hours